


Applicant: Kaisa Putkisto et al.
PCT App. No.: PCT/FI03/00183

Remarks

Claims 8–26 remain pending in the application.

Applicant believes that no new matter has been added by these amendments and that the application, as amended, is ready for examination. Favorable action thereon is respectfully solicited.

Respectfully submitted,

A handwritten signature in cursive script, reading "David R.J. Stiennon". The signature is written in dark ink and is positioned above a horizontal line.

David R.J. Stiennon, Reg. No. 33212
Attorney for Applicant
P.O. Box 1667
Madison, Wisconsin 53701-1667
(608) 250-4870
Amdtl.app/amdt

10/507240

DT09 Rec'd PCT/PTO 09 SEP 2004

In The United States Patent And Trademark Office

Applicant: Kaisa Putkisto et al.

Date: September 9, 2004

Date Filed: Simultaneously herewith

Docket No.: METSO-22

PCT App. No.: PCT/FI03/00183

For: A Grounding Electrode and a Method in Which it is Utilized


Certificate of Express Mailing

I hereby certify that this document is being deposited with
the United States Postal Service "Express Mail Post Office to
Addressee" service under 35 C.F.R. §1.10

on 9/9/04

with Mailing Label No. EV44734541645

and is addressed to the Commissioner for Patents, P.O. Box
1450, Alexandria, VA 22313-1450



Signature

David R.J. Stiennon, Reg. No. 33212

Name of applicant, assignee or Registered Representative

Marked Up Copy of Substitute Specification under 37 C.F.R. 1.125(b)(2)

TITLE OF THE INVENTION

A ~~[g]~~Grounding ~~[e]~~Electrode and a ~~[m]~~Method in ~~[which it is utilized]~~

~~[Which it is Utilized]~~

CROSS REFERENCES TO RELATED APPLICATIONS

[0001] This application is a U.S. national stage application of International application No. PCT/FI03/00183, filed Mar. 11, 2004, and claims priority on Finnish Application No. 20020479, filed Mar. 14, 2002, and on Finnish Application No. 20021651, filed Sept. 16, 2002.

5

**STATEMENT AS TO RIGHTS TO INVENTIONS MADE UNDER
FEDERALLY SPONSORED RESEARCH AND DEVELOPMENT**

[0002] Not applicable.

BACKGROUND OF THE INVENTION

[0003] The present invention relates to a grounding electrode of a process in which a moving web having a first side and a second side is arranged to serve as a substrate, and a powdery layer is arranged to be formed on the first side of the web by applying electrically charged particles on the web while the grounding electrode is arranged to be located at the second side of the web. The present invention also relates to a method for forming a powdery layer from powdery particles on a surface of a continuous web comprising steps of: Allowing the web having a first side and a second side to move between at least one charging unit of the powdery particles at the first side of the web, and at least one grounding electrode at the second side of the web being in a ground potential or another predetermined potential, applying on the first side of the web powdery particles, which are electrically charged in the charging unit, and finishing the powdery layer.

[0004] The known grounding electrodes used in this context have been stationary electrodes, such as electrically conductive plates.

[0005] A problem related to the method using the stationary grounding electrode with a moving web is that the particles of the dry powder tend to accumulate due to the stationary grounding electrode. The charged particles may tend to cake on the web at the location of the leaving edge of the grounding plate. A part of the charged particles remain in the sphere of influence of the grounding electrode, and do not move forward with the substrate. The phenomenon can be seen as a bubbling of the charged particles at the location of the edge of the stationary grounding electrode. As a consequence, an uneven powdery layer is formed on the substrate, and it can be seen as streaks on the surface of the substrate.

SUMMARY OF THE INVENTION

[0006] The device of the invention overcomes the defects of the prior art. The grounding electrode of the invention and the method of the invention are characterized in that the grounding electrode is a rotating device.

5 **[0007]** By using the rotating device the above-mentioned problems can be avoided, and a powdery layer without unevenness can be achieved. The rotating device can be for example a grounding roll, an endless conductive wire, or belt. A prerequisite for all the devices is that they must be electrically conductive at least partly.

10 **[0008]** The grounding electrode of the invention is used in a process in which electrically charged powdery particles are applied on a substrate by utilizing electric forces. The substrate is preferably a continuous web. The continuous web may be a web to be coated, or a surface onto which a film is formed and peeled off as a ready product. There is a wide variety for the material of the web; it may comprise papermaking fibers, for example chemical pulp and/or mechanical pulp, or it may be
15 plastic, metallic, or a metal-coated plastic material.

20 **[0009]** The powdery particles may comprise inorganic particles, binder particles, plastic particles, or other polymeric particles. In a final product, the powdery particles may form a coating layer, or a film layer. Typically, the coating layer is aimed to replace conventional paper coatings, and the film layer is aimed to replace conventional film layers, such as a plastic film on a paper substrate. When the
25 powdery particles are applied on the web they are substantially dry; the moisture content of the powdery particles is preferably less than 15 wt-%.

30 **[0010]** The process arrangement is as follows: The web having a first side and a second side serves as a substrate on which the powdery layer is formed. At the second side of the web there is the rotating grounding electrode, which attracts the electrically charged powdery particles intended to be applied on the first side of the web. The grounding electrode is in a ground potential or another predetermined

potential, which deviates from the zero potential. For example, if the powdery particles are treated by a negative corona the grounding electrode may have a positive potential. The rotating grounding electrode may be in contact or in close range with the second surface of the web. The grounding roll may also have an insulating surface layer to enhance the electric field.

[0011] The powdery particles are charged in a charging unit. The charging unit may comprise at least one corona charging electrode at the first side of the web, or the particles are charged by tribocharging. A combination of the corona charging and the tribocharging may be also used. The electrically charged powdery particles are applied on the web by blowing the particles from a feeding nozzle towards the web.

[0012] When there are electrode/s at the both sides of the web, and the electrodes at the first side of the web are in a different potential compared to electrodes at the second side of the web, the powdery particles are applied on the substrate in such a manner that the electrodes at the opposite sides of the substrate form an electric field in which the particles of the dry powder are blown through a feeding nozzle. The layer formed of the powdery particles is finished by a suitable manner in a final fixing device, for example by thermomechanical treatment, such as calendering. The substrate can be treated only one surface at a time, or both surfaces at the same time. It is also possible that two or more layers are formed one upon the other.

[0013] The web to be treated may advance in a continuous manner on the surface of the grounding roll during the process. The grounding roll may form a nip with a first hot roll belonging to the finishing unit, which at least partially melts a binder of the powdery material. The finishing can be finalized in the next nip/nips. The grounding roll and the following rolls can form a calender stack. The web in contact with the grounding roll is grounded or brought in a predetermined potential down to the nip formed by the grounding roll and the first hot roll. The finishing can also be finalized by using chemicals, or a suitable radiation, for example UV radiation, to fix the coating powder to the web.

BRIEF DESCRIPTION OF THE DRAWINGS

[0014] In the following, the method of the invention is explained by a drawing, which shows a schematic side view of a process step in which the grounding electrode of the invention is applied.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0015] A web W to be treated, such as a paper or plastic web, runs between a rotating grounding roll 2 and a charging electrode 1. The web W is in contact with the grounding roll 2. The charging electrode 1 can be either positive or negative. The
5 charging electrode 1 may be a corona charging electrode. Particles of a powdery material are charged by the electrode 1, and blown towards the web W by a feeding nozzle (not shown). The particles may include inorganic particles, binder particles, plastic particles, or other polymeric particles. The particles of the powdery material are attracted by the grounding roll 2, and thus a powdery layer is formed on the
10 surface of the web W.

[0016] The powdery layer, which is adhered to the web W by electrostatic forces is fixed to the web in nips formed between the grounding roll 2 and a heated hard roll 3, and the heated hard roll 3 and a resilient roll 4. The web W is directly grounded down to the first nip but it is possible that the first heated hard roll 3 is in the same
15 potential as the grounding roll 2. The powdery particles include binder particles, which melt in contact with the heated hard roll 3.

[0017] The invention is not restricted to the description above, but it may vary within the scope of the claims.

{Abstract:

~~The present invention relates to a grounding electrode of a process in which a web (W) having a first side and a second side is arranged to serve as a substrate. }~~

5

ABSTRACT OF THE DISCLOSURE

A powdery layer is ~~{arranged to be }~~formed on ~~{the}a~~ first side of ~~{the}a~~ web (W)
which serves as a substrate by applying electrically charged particles on the web
while ~~{the}a rotating~~ grounding electrode is ~~{arranged to be }~~located at ~~{the}a~~
second side of the web.~~{ The grounding electrode is a rotating device. The~~
10 ~~invention also relates to a method utilizing such a grounding electrode. }~~